


Polymer Systems Technology Limited

UK & Ireland Distributor




© 2011 - Polymer Systems Technology Limited TM
Unit 2. Network 4. Cressex Business Park,
Lincoln Road, High Wycombe, Bucks. HP12 3RF
Phone +44 (0) 1494 446610
Fax: +44 (0) 1494 528611
Web: <http://www.siliconepolymers.co.uk>
Email: sales@silicone-polymers.co.uk




PCM-7931

Vinyl Crosspolymer

Description



- Dimethyl methylvinyl copolymer trimethyl endblocked



- Dimethyl methylhydride copolymer trimethyl endblocked
- 1:1 Mix Ratio (Part A: Part B)

Applications

- As a formulary component in cosmetics application

Properties	Average Result	ASTM	NT-TM
Uncured:			
Appearance	Transparent	D2090	002
Viscosity	535 cP (535 mPas)	D1084, D2196	001
Specific Gravity, Pycnometer	0.98	D891, D1475	022
Cured: 1 hour @ 100°C (212°F)			
Bulk Gel Hardness (1" foot, 15.5 g force w/ 0.5g trigger for 5 seconds)	10.0 mm (0.40 inches)	-	036

Properties tested on a lot-to-lot basis. Do not use the properties shown in this technical profile as a basis for preparing specifications. Please contact NuSil Technology for assistance and recommendations in establishing particular specifications.

Instructions for Use

Thoroughly mix Part A with Part B in a 1:1 mix ratio by weight or volume. Increase the ratio of Part A to Part B in the initial mix for a softer gel (high penetration value) and increase the ratio of Part B to Part A for a firmer gel (lower penetration value). Deviations from the 1:1 mix ratio may change cure rates. Airless mixing, metering and dispensing equipment is recommended for production processing.

Vacuum Deaeration

Removed air entrapped during mixing by common vacuum deaeration procedure, observing all applicable safety precautions. Slowly apply vacuum, up to 28 inches Hg, to a container rated for use and of volume at least four times that of material being deaerated. Hold vacuum until presence of air is no longer evident.

Substrate Considerations

Cures in contact with most materials. Exceptions include butyl, latex, chlorinated rubbers, some RTV silicones and unreacted residues of some curing agents.

Adjustable Cure Schedule

Product cures at a wide range of cure times and temperatures to accommodate different production needs. Contact NuSil Technology for details.

Packaging

2 Pint Kit (0.91 kg)
2 Gallon Kit (7.28 kg)
10 Gallon Kit (36.4 kg)

Warranty

12 Months

Specifications

Do not use the properties shown in this technical profile as a basis for preparing specifications. Please contact NuSil Technology for assistance and recommendations in establishing particular specifications.

Warranty Information

The warranty period provided by NuSil Technology LLC (hereinafter “NuSil Technology”) is 12 months from the date of shipment when stored below 40°C in original unopened containers. Unless NuSil Technology provides a specific written warranty of fitness for a particular use, NuSil Technology’s sole warranty is that the product will meet NuSil Technology’s then current specification. NuSil Technology specifically disclaims all other expressed or implied warranties, including, but not limited to, warranties of merchantability and fitness for use. The exclusive remedy and NuSil Technology’s sole liability for breach of warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. NuSil Technology expressly disclaims any liability for incidental or consequential damages.

Warnings About Product Safety

NuSil Technology believes, to the best of its knowledge, that the information and data contained herein are accurate and reliable. The user is responsible to determine the material’s suitability and safety of use. NuSil Technology cannot know each application’s specific requirements and hereby notifies the user that it has not tested or determined this material’s suitability or safety for use in any application. The user is responsible to adequately test and determine the safety and suitability for their application and NuSil Technology makes no warranty concerning fitness for any use or purpose. NuSil Technology has completed no testing to establish safety of use in any medical application.

NuSil Technology has tested this material only to determine if the product meets the applicable specifications. (Please contact NuSil Technology for assistance and recommendations when establishing specifications.) When considering the use of NuSil Technology products in a particular application, review the latest Material Safety Data Sheet and contact NuSil Technology with any questions about product safety information.

Do not use any chemical in a food, drug, cosmetic, or medical application or process until having determined the safety and legality of the use. The user is responsible to meet the requirements of the U.S. Food and Drug Administration (FDA) and any other regulatory agencies. Before handling any other materials mentioned in the text, the user is advised to obtain available product safety information and take the necessary steps to ensure safety of use.

Patent / Intellectual Property Warning

NuSil Technology disclaims any expressed or implied warranty against the infringement of any domestic or international patent/intellectual property right. NuSil Technology does not warrant the use or sale of the products described herein will not infringe the claims of any domestic or international patent/intellectual property right covering the product itself, its use in combination with other products, or its use in the operation of any process.